



product name		Production location
Wasserstrich Alaska		Beek
A mix of Eifel and Westerwald clays forms the basis for this facing brick. By using the Waterstruck technique the brick surfaces are structured yet not sanded. By smothering the brick the typical blue-grey colour is obtained.		
Colour		
Light grey with light brown shades		
Format		
Moulding method		Waterstruck
WF: 209 x 99 x 51 mm DF: 217 x 100 x 66 mm		Between batches the average size and color may slightly differ.
Essential Characteristics - EN771-1		
 <span style="margin-left: 20px;">0620-CPR-53104</span>		
Dimensional tolerances	T2	
Range	R1	
Active Soluble Salts	S2	
Mean Compressive strength	$\geq 25 \text{ N/mm}^2$	Tested to the bed face
Normalized Compressive strength	$\geq 20 \text{ N/mm}^2$	Tested to the bed face
Dimensional stability	NPD	
Bond Strength general	$0,15 \text{ N/mm}^2$	
Bond Strength thin layer	$0,30 \text{ N/mm}^2$	
Reaction to fire	A1	Category
Water absorption	$\leq 10\% \text{ m/md}$	
Water vapour permeability	50/100	
Net dry density	$1900 \text{ kg/m}^3 \text{ (D1)}$	
Gross dry density	$1750 \text{ kg/m}^3 \text{ (D1)}$	
Thermal conductivity Lambda 50/50	$\leq 0,53 \text{ W/m.K}$	
Durability against freeze thaw	F2	
Dangerous substances	NL-BSB	According to Annex ZA 3
Other Characteristics		
Initial rate of water absorption - Non-coated Bricks	$0,5 - 1,5 \text{ kg/m}^2 \cdot \text{min (IW2)}$	Value according EN771-1:2011 - 5.3.8
Initial rate of water absorption - Coated bricks	NPD	Value according EN771-1:2011 - 5.3.8
Freeze/thaw resistance	NPD	B 27-009
Thermal conductivity Lambda 90/90	NPD	
Thermal conductivity Lambda Ui	NPD	
Thermal conductivity Lambda Ue	NPD	
		
Storage & handling		Cutting
<ul style="list-style-type: none"> <li>- Store packs on a clean surface and cover them</li> <li>- Process from multiple packs at the same time</li> <li>- Follow the Vandersanden processing guidelines</li> </ul>		Cutting with power tools may generate dust. This dust may contain silica or quartz particulate which may constitute a hazard. Persons undertaking work of this nature are advised to wear dust masks (FFP3).
*All our Coated bricks are only coated on the facing sides. Coated products are specially labeled and recognisable with a "C" logo on the top left-hand side of the packaging. Always check if using coated or non-coated bricks. Match the mortar to the specified initial water absorption.		